E-Song America, Inc. 100% RoHS Compliant Products 1901 S. Bascom Ave., Prune Yard Tower I, Suite 1225, Campbell, CA 95008 Email: sales@esongamerica.com Tel. (408) 466-5446 FAX (408) 879-9373

THERMAL INTERFACE PAD: THEA720

Characteristic

This product is made of highly conformable, low modules silicone polymer filled with Alumina filler providing excellent heat conductivity. Flame retardant UL94V0 and good

Application

-Areas where heat needs to be transferred away to the frame chassis or other type of heat spreader -Between a CPU and a heat spreader

- -Between a CD ROM drive and a heat spreader
- -Between a semiconductor and heat sink
- -Replacement for messy grease
- -Available in custom sizes and die-cut shapes/sizes

Product Structure

Polyester release film

Alumina-impregnated silicone

Inherently sticky, requiring no adhesive

•

– Polyester release film

Technical data

| ITEM | | | VALUE | TEST METHOD |
|------------------------------------|---------------------------------------|------------------------|----------------------|-------------|
| ial | Binder | | Silicone | |
| Mater | Filler | | Alumina | |
| | Liners (top and bottom) | | Polyester | |
| Mechanical properties | Thickness (mm) | Silicone pad available | 0.5 to 10 ± 0.25 | ASTM D 1000 |
| | | Release film | 0.100 | |
| | Standard size (mm) | | 210 x 300 | |
| | Color | Silicone pad | Dark Gray | Visual |
| | | Release film | Transparent | Visual |
| | Hardness (Shore OO) | | 60 | ASTM D 2240 |
| | Specific gravity (g/cm ³) | | 2.8 | ASTM D 792 |
| | Continuous usage temp. (°C) | | -60 ~ +200 | |
| Electrical properties | Dielectric constant | | 6.2 | ASTM D 150 |
| | Dielectric breakdown (kV AC) | | >8 | ASTM D 149 |
| | Volume resistivity (ohm-meter) | | $>10^{12}$ | ASTM D 257 |
| Thermal conductivity 10psi (w/m.K) | | | 2.0 | ASTM D 5470 |
| Flame Rating | | | UL94 V0 | |



